



THOR Tarp

DIV. OF

ODIN

INTERNATIONAL, INC



DURASHIELD™ 8000 SPECIFICATIONS

DuraShield 8000 is a durable, long lasting tarp meant for roughest, toughest conditions in industry and construction.

WEIGHT:	6.0 oz./yd ²
THICKNESS:	12 MIL
COATING:	1.75 MIL average, two sides (41 g/m ² , two sides)
WEAVE:	Nominal 10 by ppi (38 x 31 tapes per 10 cm), clear HDPE tapes, UV stabilized
TENSILE STRENGTH: (Grab Method)	Warp - 215 lbs. 9560 N ASTM D 5034 Weft - 175 lbs. 778 N ASTM D 5034
TEAR STRENGTH: (Tongue Method)	Warp - 60 lbs. 267 n N ASTM D 2261 Weft - 60 lbs. 267 ASTM D 2261
MULLEN BURST	350 psi 2415 kPa ASTM D 3786
UV WEATHERING:	70% to 100% strength after 2000 hrs ASTM G53
COLOR:	Silver/White
WIDTH:	Up to 144 inches

THE ABOVE PHYSICAL TEST RESULTS ARE REPRESENTATIVE DATA COLLECTED FROM A NUMBER OF PRODUCTION RUNS. RESULTS FOR AN INDIVIDUAL ROLL (BASED ON AT LEAST 3 SPECIMENS) MAY VARY FROM THE AVERAGE BY ± 10%.

To the best of our knowledge, the information contained herein is accurate. The information provided is based upon data furnished by our suppliers. However, ODIN International, Inc. assumes no liability whatsoever for the accuracy or completeness of the information contained herein. While believed to be reliable, the information of products are intended for use by skilled persons at their own risk. Final determination of suitability of any material is the sole responsibility of the user. All materials may present unknown hazards and should be used with caution. Although certain hazards are described herein, we cannot guarantee that those are the only hazards that exist.

CORPORATE HQ: P.O. Box 811 • OCONOMOWOC, WI 53066-0811 • 262-569-7171 • FAX: 262-569-1511
TOLL FREE: 1-888-ODIN-INC • 1-888-634-6462 • EMAIL: INFO@THORTARP.COM

WWW.THORTARP.COM