



THOR Tarp

DIV. OF **ODIN** INTERNATIONAL, INC



DURASHIELD™ 12000

PROPERTY	TEST METHOD(S)	VALUE
Count		Nominal 24 x 16 tapes/inch
Weight		10 oz. per sq. yd.
Tensile strength (Grab method)	ASTM D1682-64	
- MD		440 lbs.
- TD		335 lbs.
Tear strength (Tongue method)	ASTM D2261-71	
- MD		65 lbs.
- TD		65 lbs.
Mullen burst	ASTM D751	610 psi
Coating thickness		2 mil average two sides
Scrim type		Clear tapes
Color		Natural
Width		Up to 12 feet without seams- unlimited with seams (heat, sewn, extrudate)

These values are typical data are not intended as limiting specifications.